EZ ON COAT™
SAVE YOUR ROOF, SAVE YOUR MONEY

CRRC COOL ROOF RATING COUNCIL® MEMBER

MADE IN THE USA

## PRODUCT DATA SHEET

# DOT-POTHOLE FILLER

### DESCRIPTION

DOT-Pothole Filler® "c" is a blend of pumice sand, quartz, limestone, recycled rubber, gypsum and polymers used to create a liquid flexible pothole filler. DOT-Polthole Filler® "c" adheres to damp concrete surfaces. It will set in 3-5 minutes and is firm enough for traffic after 30 minutes depending on the amount of activator and weather. To match the color to its surroundings, use EZ on Coat® Paint. Pothole Filler® "c" dries sandy white, cures gray.

### RECOMMENDED USES

Designed to fill damp potholes, bridge joints, tarmacs, fill voids & cracks in concrete, and can be used on asphalt roads.

### BENEFITS

- Can be applied in warm or cold weather
- Viscosity can be adjusted
- Needs no heating
- No compaction necessary
- Non-toxic, non-hazardous
- Fast drying
- Easy placement
- Can be painted

***CONSULT ARC TECHNICAL DEPARTMENT FOR ANSWERS TO ANY QUESTIONS REGARDING USE OF THIS PRODUCT***

### TECHNICAL DATA

| | |
|---|---|
| RESIN TYPE: | Propriety Polymers |
| COVERAGE: | 231 cubic inches per gallon |
| EXTRUSION: | 0.14 inches (0.25 inches and under passing) ASTM D-1751 |
| RECOVERY: | 95% (70% is required to pass) ASTM D-1751 |
| COLOR: | Sandy White dry, Gray cured |
| PERMEABILITY: | 0.20 Perms ASTM D-96 |
| SOLIDS: | 93 - 97% +/- 2% ASTM D-1353 |
| WEIGHT: | 6.5-7 lbs. per gallon |
| VISCOSITY: | 1,000 - 1,500 cps. (Brookfield) |
| FLASH: | None ASTM D-1310 |
| POT LIFE: | 1 minute (up to 15 minutes available) |
| STORAGE: | 1 year prior to activation in unopened container. Store between 40 - 100 F |
| WORKING TIME: | Within 1 - 2 minutes |
| FULL CURE: | 72 hours |
| CLEAN-UP: | Soap & water |
| RESISTANCE TO HANDLING: | No breakage or deformation after twisting and and bending. ASTM D-1751 |
| TRAFFIC: | Open to traffic after 40 minutes, depending on activator and temperature. |
| WEATHERING: | No deleterious effect ASTM D-545, Sec 7 |

*CAUTIONS: This product must be stored in temperatures above 40 F. Keep containers covered when not in use. Avoid prolonged contact with skin. Do not take internally. Do not induce vomiting. Call a physician.*

System warranty available. When sold separate from system there is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in house and independent third party labs in order to obtain approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent, or the buyer's customer. EZ On Coat®assumes no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER GUARANTY OR WARRANTY OF ANY KIND IS MADE BY EZ On Coat®, INC. OR ITS SUBSIDIARIES, EXPRESSED OR IMPLIED, STATUORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING COSMETIC APPEARANCE, MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.